8900 Series Dissipative Rubber Mats and Rolls

8900 Series Dissipative Rubber Mats and Rolls meet ANSI/ESD S20.20 required limit and the recommendation of work surface standard ANSI/ESD S4.1. The product is constructed using a top color layer of static dissipative neoprene rubber laminated to a bottom black layer of conductive neoprene rubber. Both layers are made from vulcanized synthetic rubber, which offers resistance to oil, grease and most common solvents. They offer increased resistance to heat and hot solder as compared to vinyl or olefin materials. Non-standard sizes are available on a custom order basis. Compatible with Continuous or Constant Monitors.





8900 Table Mat Kit shown with included hardware

Available in Blue or Gray

3048 Wrist Strap Grounding System

Table Mat Kit Item Numbers

			Table Mad 1/24 heads at a s
Size	Blue	Gray	Table Mat Kit Includes: 1 Table Mat, size as specified
2' x 4' (0.6 m x 1.2 m)	<u>8900</u>	<u>8901</u>	1 <u>3048</u> Wrist Strap Grounding Syst 2 <u>3034</u> Snap Fasteners (installed)

Table Roll Item Numbers

Size	Blue	Gray
24" x 50' (0.6 m x 15.2 m)	<u>8902</u>	
30" x 50' (0.7 m x 15.2 m)	<u>8903</u>	
36" x 50' (0.9 m x 15.2 m)	<u>8904</u>	
48" x 50' (1.2 m x 15.2 m)	<u>8905</u>	<u>8906</u>



		United States of America				
Electrical Properties		Typical Value		Test Method		
Color Top Layer Resistances Surface to Ground (Rtg) Surface to Surface (Rtt)		1 x 10 ⁶ to < 1 x 10 ⁸ ohms 1 x 10 ⁶ to < 1 x 10 ⁸ ohms		ANSI/ESD S4.1 & ESD TR53 ANSI/ESD S4.1 & ESD TR53		
Conductive Bottom La Surface to Surface (Rt	•	< 1 x 10 ⁴ oł	าms	ANSI	/ESD S4.1 & ESD TR53	
					Turisal Malus	
Physical Properties	Typical Value		Other Propertie	es	Typical Value	
Material	Dual-layer rubber material		Heat Resistance	9	Does not melt or burn when coming into contact with hot solder and	
Thickness*	0.065" (1.7 mm)					
Hardness	70 +/- 5 Shore A				soldering irons	
Tolerance	Width +/- 0.250"					
Length +/- 0.250" Thickness +/- 10%			Chemical Resistance		ce Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic hydrocarbons, mineral oil, aldehydes, and	
Color* Blue, Gray (Top) Black (Bottom)						
	<u></u>				mineral oil, aldenyues, and	

Cutting Material: Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to condition for at least 4 hours before cutting to size. Always use care. Trim with a sharp knife or razor blade.

Grounding: If the material is used on top of an already properly grounded surface, grounding hardware may not be necessary. Where no properly grounded surface is available, grounding hardware is required to provide a path-to-ground.

*Color, texture and thickness may vary between lots and mills.

Slight embossed

Impers	Table Dall Includes						
Blue Gray 8902	Table Roll Includes: 1 Table Roll, size as specified	Limited Lifetime Warranty: SCS warrants for one year that 8900 Series matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by <u>SCS Limited Warranty</u> .					
<u>8903</u> <u>8904</u>		RoHS 3, REACH, and Conflict Minerals Statement None of the RoHS 3 restricted materials or REACH substances of very Conflict Minerals are intentionally added in manufacturing this product. 2015/853 ammending Annex II of the RoHS 2 Directive 2011/65/EU and See <u>SCS Warranty, Limitation of Liability and Remedies.</u>	Ref: European Union Direc	tive (EU)			
<u>8905</u> <u>8906</u>		Specifications and procedures subject to change without notice.					
		8900 SERIES DISSIPATIVE RUBBER MATS AND ROLLS					
S	CS	926 JR Industrial Drive, Sanford, NC 27332 WEB SITE: <u>StaticControl.com</u> PHONE: EAST: (919) 718-0000 WEST: (909) 627-9634	DRAWING NUMBER 8900	DATE September 2018			

Texture*



amines



© 2018 DESCO INDUSTRIES INC Employee Owned